

# DuraClear Sealant Instructions

DuraClear Sealant is for use as a protective coating over Water Transfer/Hydro Graphics. DuraClear penetrates the film and creates a better bond between the graphics and the firearm. DuraClear creates a protective coating that will not scratch or chip. It will keep your graphics from wearing or rubbing off over time.

- 1) Clean firearm with LCW NST Cleaner/Degreaser (Do NOT use any organic solvents)
- 2) Allow to completely dry
- 3) Shake DuraClear for at least three minutes after hearing the rattling ball
- 4) Mix DuraClear and Hardener in a ratio of 12:1
- 5) Apply DuraClear with any air brush or small spray gun to a test spot or on a scrap piece.
- 6) Once you are sure you are not experiencing any difficulties spraying, spray your entire firearm.
- 7) Clean your spray equipment with DuraCoat Reducer
- 8) Allow DuraClear to dry overnight before reassembling or handling.
- 9) DuraClear will take several weeks to be fully cured but your firearm can be carefully used before then. Do NOT apply any oils or cleaners to the firearm during the first few weeks.

## Troubleshooting:

- If you are experiencing fogginess or roughness, try applying in heavier coats or holding your sprayer closer to the part you are spraying. Weather may affect DuraClear so if it is very humid we recommend waiting until there is less moisture in the air.

- We always recommend testing the DuraClear on a scrap piece of metal or plastic prior to applying it to your firearm.