



Girl's Guide to Guns.com DuraCoat® Finishing Kit Instructions

- 1) Prep your metal, plastic or wood parts by spraying the TruStrip™ Cleaner/Degreaser causing the oil and grime to run off. Then scuff with the enclosed pad keeping the pad saturated with TruStrip.
- 2) Shake the DuraCoat® bottle for three minutes after hearing the mixing ball then pour the entire contents into the glass jar. Add the entire contents of the enclosed DuraCoat® Hardener. Screw the white cap onto the jar and shake for one minute. Remove the cap and screw on the Preval sprayer.
- 3) Spray your parts in thin, even passes. Allow the part to dry for 5 minutes in between coats. Apply approximately three coats.
- 4) Hang your parts to dry for at least 30 minutes but no more than seven days.
- 5) Empty any remaining contents of the Preval jar. Clean out the Preval Sprayer using the DuraCoat® Reducer. Pour the entire bottle of Reducer into the jar and spray until clear.
- 6) Shake the DuraPearl™ bottle for three minutes then pour the entire contents into the glass jar. Add DuraPearl™ Hardener. Screw the white cap onto the jar and shake for one minute. Remove the cap and screw on the Preval sprayer.
- 7) Spray your parts in thin, even passes. Allow the part to dry for at least 5 minutes in between coats. Apply as much or as little as desired but do not exceed three coats.
- 8) Hang your parts to dry. It may take longer for the DuraPearl™ to dry than the DuraCoat®. This is normal.
- 9) Allow to dry at least overnight before assembly. Allowing your parts to dry longer is better. Only expose the parts to light use during the 3-4 week cure time. Once fully cured, your parts will not scratch or chip and will be resistant to all solvents and cleaners.